

Selecting your Coating and how many coats needed - On New or Unsurfaced Pools

For Smooth Concrete Surface			
System	Primer	Coating	# of Coats
Epoxy*	Poxoprime II	Zeron	1
Epoxy*	Poxoprime II	Poxolon 2	2
Chlorinated Rubber	None	Paralon 2	2
Synthetic Rubber	None	Optilon	2
Acrylic	None	Hydrolon	2
For Plaster Surface			
System	Primer	Coating	# of Coats
Epoxy*	Poxoprime II	Zeron	1
Epoxy*	Poxoprime II	Poxolon 2	2
Chlorinated Rubber	None	Paralon 2	2
Sythetic Rubber	None	Optilon	2
Acrylic	None	Hydrolon	2
* Use Gunzite on all rough plaster and concrete and on sandblasted surfaces.			
For Gunite Surface			
System	Primer	Coating	# of Coats
Epoxy	Gunzite	Zeron	1
For Aluminum Surface			
System	Primer	Coating	# of Coats
Epoxy	Bonderite	Zeron	1
Epoxy	Bonderite	Poxolon 2	2
For Steel Surface			
System	Primer	Coating	# of Coats
Epoxy	#219 Steel Primer	Zeron	1
Epoxy	#220 Steel Primer	Poxolon 2	2
Olympic Pool Products are not recommended for stainless steel.			
For Fiberglass Surface			
System	Primer	Coating	# of Coats
Epoxy	Gunzite	Zeron	1
Epoxy	Gunzite	Poxolon 2	2
One coat of Zeron may replace two coats of Poxolon 2 in all cases where epoxy is used.			